

PRODUCT DESCRIPTION

FPF 613 is a maleic rosin, ester with glycerol.

CHARACTERISTICS

Yellow solid.

Good nitrocellulose compatibility.

Promotes high gloss.

Promotes good hardness.

Compatibility:

- Nitrocellulose ½ seg.....almost complete.

Solubility:

- *n*-butanol acetate.....complete;
- *n*-butanol.....insoluble;
- methylethyl ketone (MEK).....complete;
- toluene.....complete;
- xylene.....complete;
- white spirit.....insoluble.

PRODUCT SPECIFICATIONS¹

	Product Specification	Typical Properties	Units
Acid Number	40 max	30	mg KOH/g
Colour Gardner (50%, Toluene)	10 max	7	-----
Softening Point (R&B)	125-135	130	° C

APPLICATIONS

Resin specially recommended for:

- Nitrocellulose primers and varnishes;
- Cellulose enamels.

FORM OF SUPPLY

Flakes/Pearls: 25 Kg bags.

SHELF LIFE

Up to twelve months under normal storage conditions.

¹Analytical Methods are available on request

The information in this Technical Data Sheet is, to the best of our knowledge, true and accurate, but since the conditions of use are beyond our control, no warranty is given or to be implied in respect of such information. We are, at all times, willing to study customer's specific outlets involving our products in order to enable their most effective use.